



27-08-25
SCHEDA TECNICA

Liquid Acrygel 13

Modo d'uso: Stendere liquid acrygel per allungare e realizzare la struttura .Polimerizzare in lampada uv 120 secondi e lampada led 60 secondi.

Ingredienti:

INGREDIENTS / INCI	CAS
Urethane Acrylate Oligomer	71549-84-3
ISOBORNYL METHACRYLATE	7534-94-3
Aliphatic Urethane Diacrylate	n/a
BIS-HEA POLY(1,4-BUTANEDIOL)- 9/IPDI COPOLYMER	n.a.
SILICA CAPRYLYL SILYLATE	92797-60-9
Methyl Benzoylformate	15206-55-0
Aliphatic Urethane Acrylate	n/a
Ethylene Glycol Diacrylate	2274-11-5
Ethylhexyl Acrylate	103-11-7
PEG200 Dimethacrylate	25852-47-5
PEG-4 Trimethylolpropane Triacrylate	28961-43-5
Silica Dimethyl Silylate	68611-44-9
ETHYLPHENYL TRIMETHYLBENZOYL PHOSPHINATE	84434-11-7
Polyester Resin	n/a
P-Hydroxyanisole	150-76-5
Isopropylidenediphenyl Bisoxhydroxypropyl Methacrylate	1565-94-2
Modified Polysiloxane	n/a
Hydroquinone	123-31-9
BHT	128-37-0
Triethylene Glycol Dimethacrylate	109-16-0
CI 77891	13463-67-7
CI 77002	1332-73-6
CI 71105	4424-06-0
CI 19140	12225-21-7
CI 77499	12227-89-3
CI 12490	6410-41-9



Avvertenze: Provoca irritazione cutanea. Può provocare una reazione allergica cutanea. Provoca grave irritazione oculare

Dichiarazioni precauzionali:

P261 - Evitare di respirare la polvere/i fumi/i gas/la nebbia/i vapori/gli aerosol.

P280: Indossare guanti/indumenti protettivi/proteggere gli occhi/proteggere il viso/proteggere l'udito/...

P302+352: IN CASO DI CONTATTO CON LA PELLE: lavare abbondantemente con acqua.

P305 + P351 + P338 IN CASO DI CONTATTO CON GLI OCCHI: Sciacquare accuratamente per parecchi minuti. Togliere le eventuali lenti a contatto se è agevole farlo. Continuare a sciacquare.

P321 Trattamento specifico (vedere istruzioni su questa etichetta).

P362 + P364 – Togliere tutti gli indumenti contaminati e lavarli prima di indossarli nuovamente.